


Murfor[®] Compact A-80

Masonry reinforcement



General description

Murfor[®] Compact masonry reinforcement on a roll, consists of steel cords connected with an interwoven fiberglass roving.

Murfor[®] Compact A-80

A mesh consisting of 14 steel cords.


Application

Murfor[®] Compact A-80, made of galvanized Steel, is suitable for Autoclaved Aerated Concrete (AAC) masonry exposed to a dry environment (exposure class MX1, compliant with Eurocode 6 / EN 845-3).

Murfor[®] Compact A-80 is suitable for all mortar joints with thickness between 3 mm and 12 mm.

Dimensions

Width	mm	w	80
Pitch _{short}	mm	a	5
Pitch _{long}	mm	b	10
Step	mm	c	33
Thickness	mm	e	1.75
Length	m/roll	L	30
Weight	kg/roll		2.66



Technical specifications

Steel section

Longitudinal cord	mm ²	0.69
Total	mm ²	9.66
Characteristic Yield strength	MPa	1770
Young's modulus	GPa	180
Strain - Agt	%	2.2
Coating reference	EN845-3	R 20


Product certificates



Packaging units



Per box
3 rolls
90 meters



Per pallet
(900x1200mm)
36 boxes
3240 meters

Handling



KEEP DRY

Contact:

For inquiries and orders visit
www.bekaert.com/contactconstruction

For EC Declaration of Performance visit
www.bekaert.com/doc/Murfor_Compact

Any other specific document or certificate can be found on
www.bekaert.com/masonry/downloads