

Brickforce® SBF30

Product Data Sheet

General description

Brickforce® SBF is a ladder type masonry reinforcement element that consists of two longitudinal wires which are welded together by means of a cross wire. The cross wire is welded to the longitudinal wires in the same plane.


Application

Brickforce® SBF (stainless steel) is suitable for masonry that is exposed to **dampness** (e.g. facades) or an **aggressive** environment (MX2, MX3, MX4 as per Eurocode 6 / EN 845-3, type in consultation with Bekaert) MX1, compliant with Eurocode 6 / EN845-3).


- A galvanized version Brickforce® GBF is available for use in a dry environment (MX1 as per Eurocode 6 / EN 845-3). Please contact us for further details.

Brickforce® SBF is suitable for mortar joints (10 to 12 mm thick).

- For thin joints (glued brick systems or thin joint brickwork, Bekaert offers Bricktor®. Please contact us for further details.



Geometry




Dimensions and weights

Material	w	pitch	ø _{longitudinal}	profile _{longitudinal}	ø _{cross-wire}	length	weight
	a	b	c		d	L _{nom}	
-	mm	mm	mm	mm	mm	mm	kg/pc
Brickforce® SBF30W60	60	450	3,00	2,75 x 3,0	2,5	2700	0,314
Brickforce® SBF30W100	100	450	3,00	2,75 x 3,0	2,5	2700	0,321
Brickforce® SBF30W150	150	450	3,00	2,75 x 3,0	2,5	2700	0,331
Brickforce® SBF30W175	175	450	3,00	2,75 x 3,0	2,5	2700	0,335

Technical specifications

Material	A _{longitudinal}	A _{cross-wire}	A _{TOTAL ex cross-wire}	R _{p0.2}	EN 845-3 mat coat ref	Zinc (1)
-	mm ²	mm ²	mm ²	N/mm ²		g/m ²
Brickforce® SBF30W60	7,07	4,9	14,14	500	R3	NA
Brickforce® SBF30W100	7,07	4,9	14,14	500	R3	NA
Brickforce® SBF30W150	7,07	4,9	14,14	500	R3	NA
Brickforce® SBF30W175	7,07	4,9	14,14	500	R3	NA

(1) on round wire before any subsequent processing




Packaging

- Elements are packed in bundles of 20 units
- The bundles are stacked on battens.
- The number of bundles per pallet depends on the width of the element (see table below)
- Each bundle has a product label


Packaging units

Material	Per bundle	Per bundle	Per pallet	Per pallet	Per pallet
	pcs	lm	bundles	units	lm
Brickforce® SBF30W60	20	54,0	119	2380	6426,0
Brickforce® SBF30W100	20	54,0	70	1400	3780,0
Brickforce® SBF30W150	20	54,0	49	980	2646,0
Brickforce® SBF30W175	20	54,0	42	840	2268,0


Storage instructions



STORE DRY



RIGHT



WRONG

Certificates

- CE, compliant with EN 845-3. The document "EC Declaration of Conformity" is available upon request

Bekaert Ltd.
 The Gateway Business centre
 Unit 7, 5 Leeds Road
 Sheffield S9 3TY, UK
 T +44 1142 427 489
 F +44 1142 427 490
 building.uk@bekaert.com

NV Bekaert SA
 Bekaertstraat 2
 8550 Zwevegem
 Belgium
 T +32 56 76 72 92
 F +32 56 76 72 90
 infobuilding@bekaert.com
 http://brickforce.bekaert.com

