

Dramix® 3D

55/60BL

Aspect ratio Length Bright Loose

Concrete Reinforcement



Original anchorage

Dramix® 3D is the cost-efficient fiber for standard statically indeterminate concrete structures that are subjected to regular static, fatigue and dynamic loadings.

Material properties

Nom. tensile strength:
162 ksi (1,115 MPa)
 Young's modulus:
30,458 ksi (210,000 MPa)
 Strain at ultimate strength:
0.8 %

Fiber network

1,085 fibers/lb (2,392 fibers/kg)

Geometry

Fiber family



Length (l) * / Diameter




Aspect ratio (l/d) * : **55**

* Indicative value


Packaging

BAGS:
44 lb (20 kg)



BIG BAG:
1,760 lb (800 kg)

Handling



NO STACKING



KEEP DRY

Product certificates*



System certificates*

Dramix® plants are ISO 9001 and ISO 14001 certified.



Product conformity

Dramix conforms to:
 ASTM A820-type I,
 EN 14889-1,
 ISO 13270 class A

Contact us:

For inquiries and orders on <https://construction.bekaert.com/contact-us>



For recommendations on stacking, handling, dosing and mixing, visit <https://construction.bekaert.com/dosing>

Any other specific document or certificate can be found on <https://construction.bekaert.com/resources>

* Product and system certificates are plant specific.