

Dramix[®] 3D

65/50BL

Aspect ratio Length Bright Loose

Concrete Reinforcement



Original anchorage

Dramix[®] 3D is the cost-efficient fiber for standard statically indeterminate concrete structures that are subjected to regular static, fatigue and dynamic loadings.

Material properties

Nom. tensile strength:
178 ksi (1,225 MPa)
 Young's modulus:
30,458 ksi (210,000 MPa)
 Strain at ultimate strength:
0.8 %

Fiber network

2,541 fibers/lb (5,602 fibers/kg)

Geometry

Fiber family



Length (l) * / Equivalent Diameter (d)

← 2.0 in. (50 mm) →



Aspect ratio (l/d) * : **65**


* Indicative value

Packaging

BAGS:
44 lb
(20 kg)



Handling



NO STACKING



KEEP DRY

Product certificates*



System certificates*

Dramix[®] plants are
 ISO 9001 and
 ISO 14001 certified.



Product conformity

Dramix conforms to:
 ASTM A820 type I, EN 14889-1,
 ISO 13270 class A
 Intended for use in concrete
 complying with ASTM C1116,
 Section 4.1.1

Contact us:

For inquiries and orders on
<https://construction.bekaert.com/contact-us>



For recommendations on stacking, handling,
 dosing and mixing, visit
<https://construction.bekaert.com/dosing>

Any other specific document or certificate
 can be found on
<https://construction.bekaert.com/resources>

* Product and system certificates are plant specific.