


Dramix<sup>®</sup> 3D

# **Concrete Reinforcement**



#### **Material properties**

Nom. tensile strength: 445 ksi (3,070 MPa) Young's modulus: 30,458 ksi (210.000 MPa) Strain at ultimate strength: 0.8 %

**Fiber network** 16,205 fibers/lb (35,726 fibers/kg)

**Product certificates\*** 



# **Original anchorage**

Dramix<sup>®</sup> 3D is the cost-efficient fiber for standard statically indeterminate concrete structures that are subjected to regular static, fatigue and dynamic loadings.

Aspect ratio

# **High performant strength**

Dramix<sup>®</sup> 3D Premium is a high performant fiber to create optimal ductility in high strength concrete.

## Glue technology for threedimensional reinforcement

Glued


80/30BGP

Bright

Length

Dramix<sup>®</sup> steel fibers are bundled with water-soluble glue. The glue helps to avoid fiber balling during mixing and ensures a homogeneous distribution of fibers throughout the concrete mix.

Premium



\* Indicative value

System certificates\*

ISO 14001 certified.

**Product conformity** 

13270 Class A.

Dramix<sup>®</sup> conforms to ASTM A820. EN 14889-1 and ISO

Dramix<sup>®</sup> plants are ISO 9001 and

#### Packaging BAGS: 44 lb (20 kg) 3D 3D BIG BAG: 2.425 - 2.645 lb (1,100 - 1,200 kg)

#### Handling





# **Contact us:**

For inquiries and orders on https://construction.bekaert.com/contact



For recommendations on stacking, handling, dosing and mixing, visit www.bekaert.com/dosingfibers

Any other specific document or certificate can be found on www.construction.bekaert.com/ resources

\* Product and system certificates are plant specific.

#### Bekaert reserves the right to modify, discontinue or rebrand this product at any time with or without notice. All information contained herein is general and may not be complete. For further details, please contact the local Bekaert office.