

Dramix<sup>®</sup> 3D

### **Concrete Reinforcement**



#### **Original anchorage**

Dramix<sup>®</sup> 3D is the cost-efficient fiber for standard statically indeterminate concrete structures that are subjected to regular static, fatigue and dynamic loadings.

Aspect ratio

80/30<mark>S</mark>L

Length


Stainless

Loose

Material properties

Nom. tensile strength: 290 ksi (2,000 MPa) Young's modulus: 30,458 ksi (210.000 MPa) Strain at ultimate strength: 0.8 %

Fiber network 16,205 fibers/lb (35,726 fibers/kg)



Aspect ratio (I/d) \* : 80

\* Indicative value

# Packaging BAGS: 44 lb (20 kg)



### Handling





Product certificates\*



## System certificates\*

Dramix<sup>®</sup> plants are ISO 9001 and ISO 14001 certified.



**Product conformity** Dramix<sup>®</sup> conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A. **Contact us:** 

For inquiries and orders on www.construction.bekaert.com/contact



For recommendations on stacking, handling, dosing and mixing, visit www.bekaert.com/dosingfibers

Any other specific document or certificate can be found on www.construction.bekaert.com/ resources

\* Product and system certificates are plant specific.

Datasheet\_Dramix 3D 8030SL\_EN-US\_20231205

Bekaert reserves the right to modify, discontinue or rebrand this product at any time with or without notice. All information contained herein is general and may not be complete. For further details, please contact the local Bekaert office.