

Dramix® 4D

65/50BL


Aspect ratio

Length

Bright

Loose

Concrete Reinforcement



Optimized anchorage

Dramix® 4D provides optimal crack control for standard statically indeterminate concrete structures that are subjected to regular static, fatigue and dynamic loadings with high serviceability requirements.

Material properties

Nom. tensile strength:
1.800 (N/mm²)
Young's modulus:
210.000 (N/mm²)
Strain at ultimate strength:
0,8 %

Minimum EN 14889-1 dosage

18 kg/m³

Fibre network

5.183 m/m³ at 18 kg/m³
5.382 fibres/kg

Geometry

fibre family



Length (l) * / Diameter (d)



Aspect ratio (l/d): 65


* Indicative value

Packaging

BAGS:
20 kg



Handling



NO STACKING



KEEP DRY

Product certificates*

System certificates*

Dramix® plants are ISO 9001 and ISO 14001 certified.



Product conformity

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

Contact us:

For inquiries and orders on www.construction.bekaert.com/contact



For recommendations on stacking, handling, dosing and mixing, visit www.bekaert.com/dosingfibers

Any other specific document or certificate can be found on www.construction.bekaert.com/resources

* Product and system certificates are plant specific.