


# Dramix® 5D

# 65/60BG

Aspect ratio      Length      Bright      Glued

## Concrete Reinforcement



### Ultimate anchorage

Dramix® 5D remains firmly anchored inside the concrete. Similar to rebar, the wire slowly elongates taking up tensile stresses. This fiber is the perfect solution for structural applications.

### Glue technology for three-dimensional reinforcement

Dramix® steel fibers are bundled with water-soluble glue. The glue helps to avoid fiber balling during mixing and ensures a homogeneous distribution of fibers throughout the concrete mix.

### Material properties

Nom. tensile strength:  
**334 ksi (2,300 MPa)**  
 Young's modulus:  
**30,458 ksi (210,000 MPa)**  
 Strain at ultimate strength:  
**6.0 %**

### Fiber network

**1,417 fibers/lb (3,124 fibers/kg)**

### Geometry

Fiber family



Length (l) \* / Diameter




Aspect ratio (l/d) \* : **65**

\* Indicative value


### Packaging

BAGS:  
**22 / 44 lb**  
**(10 / 20 kg)**



BIG BAG:  
**2,425 - 2,645 lb**  
**(1,100 - 1,200 kg)**

### Handling



NO STACKING



KEEP DRY

### Product certificates\*



### System certificates\*

Dramix® plants are ISO 9001 and ISO 14001 certified.



### Product conformity

Dramix conforms to:  
 ASTM A820-type I,  
 EN 14889-1,  
 ISO 13270 class A

### Contact us:

For inquiries and orders on <https://construction.bekaert.com/contact-us>



For recommendations on stacking, handling, dosing and mixing, visit <https://construction.bekaert.com/dosing>

Any other specific document or certificate can be found on <https://construction.bekaert.com/resources>

\* Product and system certificates are plant specific.