



Aspect ratio

Length

Bright

Glued

Premium

DATASHEET

Characteristics

Material properties

Nom. tensile strength: 319 ksi (2,200 MPa)
 Young's modulus: 29,000 ksi (200,000 MPa)
 Strain at ultimate strength: 0.8 %

Geometry

Fiber family **4D**
 Length (l) 2.4 in. (60 mm)
 Diameter (d) 0.03 in. (0.75 mm)
 Aspect ratio (l/d) 80

Minimum EN 14889-1 dosage

17 lb/yd³ (10 kg/m³)

Fiber network

7,221 ft/yd³ at 17 lb/yd³ (2,879) m/m³ at 10 kg/m³
 2,106 fibers/lb (4,644 fibers/kg)

Dramix® family

3D Typical SFRC applications
 4D Supreme serviceability control
 5D Advanced structural applications

	5D	4D	3D
Tensile strength			
Wire ductility			
Anchorage strength			

Product certificates *



* Product certificates are plant specific.

Product conformity

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

System certificates



All Dramix® plants are ISO 9001 and ISO 14001 certified.

Packaging



BAGS
 44 lb (20 kg)



BIG BAG
 1,760 -2,420 lb (800 - 1,100 kg)

Handling



DRAMIX® 4D 80/60BGP

Optimized anchorage

Dramix® 4D provides optimal crack control for standard statically indeterminate concrete structures that are submitted to regular static, fatigue and dynamic loadings with high serviceability requirements.

Glue technology for three-dimensional reinforcement

Dramix® steel fibers are bundled with water-soluble glue. The glue helps avoiding fiber balling during mixing and ensures a homogeneous distribution of fibers throughout the concrete mix.

The high performant strength

Dramix® 4D Premium is a high performant fiber to create optimal ductility in high strength concrete.

Bekaert construction support

You can count on our support for each step of your project, from concept design to on-site quality support. Our services include recommendations on slab design, construction detailing, concrete optimization and automatic total quality control procedures. We are also happy to share our knowledge with you and your team.

Feel free to ask us for a workshop or training on the topic of steel fiber reinforcement in your offices.

For recommendations on handling, dosing and mixing visit www.bekaert.com/dosingdramix. Any other specific document or certificate can be found on www.bekaert.com/dramix/downloads.