



Aspect ratio

Length

#N/A

Loose

DATASHEET

Characteristics

Material properties


Nom. tensile strength: 2.000 (N/mm<sup>2</sup>)  
 Young's modulus: 200.000 (N/mm<sup>2</sup>)  
 Strain at ultimate strength: 0,8 %

Geometry

fibres family

Length (l) 30 mm

Diameter (d) 0,38 mm



Minimum EN 14889-1 dosage

20 kg/m<sup>3</sup>

Fibre network

22.436 m/m<sup>3</sup> at 20 kg/m<sup>3</sup>  
 35.726 fibres/kg

Dramix® family

3D Typical SFRC applications  
 4D Supreme serviceability control  
 5D Advanced structural applications

	5D	4D	3D
Tensile strength	██████████	██████████	██████████
Wire ductility	██████████	██████████	██████████
Anchorage strength	██████████	██████████	██████████

Product certificates\*



\* Product certificates are plant specific.

Product conformity

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

System certificates



All Dramix® plants are ISO 9001 and ISO 14001 certified.

Packaging



BAGS  
20 kg



BIG BAG  
800 - 1.100 kg

Handling



DRAMIX® 3D 80/30SL

The original anchorage

Dramix® 3D is the cost-efficient fibre for standard statically indeterminate concrete structures that are submitted to regular static, fatigue and dynamic loadings.

Bekaert construction support

You can count on our support for each step of your project, from concept design to on-site quality support. Our services include recommendations on slab design, construction detailing, concrete optimization and automatic total quality control procedures. We are also happy to share our knowledge with you and your team.

Feel free to ask us for a workshop or training on the topic of steel fibre reinforcement in your offices.

For recommendations on handling, dosing and mixing visit [www.bekaert.com/dosingdramix](http://www.bekaert.com/dosingdramix). Any other specific document or certificate can be found on [www.bekaert.com/dramix/downloads](http://www.bekaert.com/dramix/downloads).