



4D **55/60** **BL**

Aspect ratio

Length

Bright

Loose





DATASHEET

Characteristics

Material properties

Nom. tensile strength: 210.30472 ksi (1450 MPa)
 Young's modulus: 29000 ksi (200000 MPa)
 Strain at ultimate strength: 0.8 %

Geometry

Fiber family **4D** 
 Length (l) 2.3622 in. (60 mm) 
 Diameter (d) 0.041339 in. (1.05 mm) 
 Aspect ratio (l/d) 55 

Minimum EN 14889-1 dosage

30 lb/yd³ (18 kg/m³)

Fiber network

6631 ft/yd³ at 30 lb/yd³ (2644 m/m³ at 18 kg/m³)
 1049 fibers/lb (2313 fibers/kg)

Dramix® family

3D Typical SFRC applications
 4D Supreme serviceability control
 5D Advanced structural applications

	5D	4D	3D
Tensile strength			
Wire ductility			
Anchorage strength			

Product certificates *



* Product certificates are plant specific.

Product conformity

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

System certificates



All Dramix® plants are ISO 9001 and ISO 14001 certified.

Packaging



BAGS
44 lb (20 kg)



BIG BAG
2,420 lb (1,100 kg)

Handling



DRAMIX® 4D 55/60BL

Optimized anchorage

Dramix® 4D provides optimal crack control for standard statically indeterminate concrete structures that are submitted to regular static, fatigue and dynamic loadings with high serviceability requirements.

Bekaert Bekaert construction support

You can count on our support for each step of your project, from concept design to on-site quality support. Our services include recommendations on slab design, construction detailing, concrete optimization and automatic total quality control procedures. We are also happy to share our knowledge with you and your team.

Feel free to ask us for a workshop or training on the topic of steel fiber reinforcement in your offices.

For recommendations on handling, dosing and mixing visit www.bekaert.com/dosingdramix. Any other specific document or certificate can be found on www.bekaert.com/dramix/downloads.