



Aspect ratio

Length

Bright

Loose

DATASHEET

Characteristics

Material properties

Nom. tensile strength: 261 ksi (1,800 MPa)
 Young's modulus: 29,000 ksi (200,000 MPa)
 Strain at ultimate strength: 0.8 %

Geometry

Fiber family **4D**

Length (l) 2.0 in. (50 mm)

Diameter (d) 0.03 in. (0.75 mm)

Aspect ratio (l/d) 65

Minimum EN 14889-1 dosage

34 lb/yd³ (20 kg/m³)

Fiber network

14,445 ft/yd³ at 34 lb/yd³ (5,759 m/m³ at 20 kg/m³)
 2,441 fibers/lb (5,382 fibers/kg)

Dramix® family

3D Typical SFRC applications
 4D Supreme serviceability control
 5D Advanced structural applications

| | 5D | 4D | 3D |
|--------------------|----|----|----|
| Tensile strength | | | |
| Wire ductility | | | |
| Anchorage strength | | | |

Product certificates *



* Product certificates are plant specific.

Product conformity

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

System certificates



All Dramix® plants are ISO 9001 and ISO 14001 certified.

Packaging



BAGS
44 lb (20 kg)



BIG BAG
1,433 lb (650 kg)

Handling



DRAMIX® 4D 65/50BL

Optimized anchorage

Dramix® 4D provides optimal crack control for standard statically indeterminate concrete structures that are submitted to regular static, fatigue and dynamic loadings with high serviceability requirements.

Bekaert construction support

You can count on our support for each step of your project, from concept design to on-site quality support. Our services include recommendations on slab design, construction detailing, concrete optimization and automatic total quality control procedures. We are also happy to share our knowledge with you and your team.

Feel free to ask us for a workshop or training on the topic of steel fiber reinforcement in your offices.

For recommendations on handling, dosing and mixing visit www.bekaert.com/dosingdramix. Any other specific document or certificate can be found on www.bekaert.com/dramix/downloads.