



**5D** **65/60** **BG**

Aspect ratio

Length

Bright

Glued

**DATASHEET**

**Characteristics**

**Material properties**

Nom. tensile strength: 334 ksi (2,300 MPa)  
 Young's modulus: 29,000 ksi (200,000 MPa)  
 Strain at ultimate strength: 6,0 %

**Geometry**

Fiber family **5D**   
 Length (l) 2.4 in. (60 mm)   
 Diameter (d) 0.04 in. (0.9 mm)   
 Aspect ratio (l/d) 65

**Minimum EN 14889-1 dosage**

25 lb/yd<sup>3</sup> (15 kg/m<sup>3</sup>)

**Fiber network**

7,221 ft/yd<sup>3</sup> at 25 lb/yd<sup>3</sup> (2,999 m/m<sup>3</sup> at 15 kg/m<sup>3</sup>)  
 1,417 fibers/lb (3,124 fibers/kg)

**Dramix® family**

3D Typical SFRC applications  
 4D Supreme serviceability control  
 5D Advanced structural applications

|                    | 5D         | 4D         | 3D         |
|--------------------|------------|------------|------------|
| Tensile strength   | ██████████ | ██████████ | ██████████ |
| Wire ductility     | ██████████ | ██████████ | ██████████ |
| Anchorage strength | ██████████ | ██████████ | ██████████ |

**Product certificates \***



\* Product certificates are plant specific.

**Product conformity**

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

**System certificates**



All Dramix® plants are ISO 9001 and ISO 14001 certified.

**Packaging**



**BAGS**  
 22 / 44 lb  
 (10 / 20 kg)



**BIG BAG**  
 1,760 -2,420 lb  
 (800 - 1,100 kg)

**Handling**



**DRAMIX® 5D 65/60BG**

**Ultimate anchorage**

Dramix® 5D remains firmly anchored inside the concrete. Similar to rebar, the wire slowly elongates taking up tensile stresses. This fiber is the perfect solution for structural applications.

**Glue technology for three-dimensional reinforcement**

Dramix® steel fibers are bundled with water-soluble glue. The glue helps avoiding fiber balling during mixing and ensures a homogeneous distribution of fibers throughout the concrete mix.

**Bekaert construction support**

You can count on our support for each step of your project, from concept design to on-site quality support. Our services include recommendations on slab design, construction detailing, concrete optimization and automatic total quality control procedures. We are also happy to share our knowledge with you and your team.

Feel free to ask us for a workshop or training on the topic of steel fiber reinforcement in your offices.

For recommendations on handling, dosing and mixing visit [www.bekaert.com/dosingdramix](http://www.bekaert.com/dosingdramix). Any other specific document or certificate can be found on [www.bekaert.com/dramix/downloads](http://www.bekaert.com/dramix/downloads).