



5D **65/60** **GG**

Aspect ratio

Length

Galvanized

Glued

DATASHEET

Characteristics

Material properties

Nom. tensile strength: 334 ksi (2,300 MPa)
 Young's modulus: 29,000 ksi (200,000 MPa)
 Strain at ultimate strength: 6,0 %

Geometry

Fiber family **5D**
 Length (l) 2.4 in. (60 mm)
 Diameter (d) 0.04 in. (0.9 mm)
 Aspect ratio (l/d) 65

Minimum EN 14889-1 dosage

25 lb/yd³ (15 kg/m³)

Fiber network

7,522 ft/yd³ at 25 lb/yd³ (2,999 m/m³ at 15 kg/m³)
 1,417 fibers/lb (3,124 fibers/kg)

Dramix® family

3D Typical SFRC applications
 4D Supreme serviceability control
 5D Advanced structural applications

	5D	4D	3D
Tensile strength			
Wire ductility			
Anchorage strength			

Product certificates *



* Product certificates are plant specific.

Product conformity

Dramix® conforms to ASTM A820, EN 14889-1 and ISO 13270 Class A.

System certificates



All Dramix® plants are ISO 9001 and ISO 14001 certified.

Packaging



BAGS
 22 / 44 lb
 (10 / 20 kg)



BIG BAG
 1,760 -2,420 lb
 (800 - 1,100 kg)

Handling



DRAMIX® 5D 65/60GG

Ultimate anchorage

Dramix® 5D remains firmly anchored inside the concrete. Similar to rebar, the wire slowly elongates taking up tensile stresses. This fiber is the perfect solution for structural applications.

Glue technology for three-dimensional reinforcement

Dramix® steel fibers are bundled with water-soluble glue. The glue helps avoiding fiber balling during mixing and ensures a homogeneous distribution of fibers throughout the concrete mix.

Bekaert construction support

You can count on our support for each step of your project, from concept design to on-site quality support. Our services include recommendations on slab design, construction detailing, concrete optimization and automatic total quality control procedures. We are also happy to share our knowledge with you and your team.

Feel free to ask us for a workshop or training on the topic of steel fiber reinforcement in your offices.

For recommendations on handling, dosing and mixing visit www.bekaert.com/dosingdramix. Any other specific document or certificate can be found on www.bekaert.com/dramix/downloads.